

# التأييس بالفلم

## Film coating Tablets



1

تكنولوجيا صيدلانية 1

د. مصطفى عبد الإله بيش

دكتوراه في التكنولوجيا الصيدلية

2

تكنولوجيا صيدلانية 1

Lecture	المحاضرة	الأسبوع
Pills	الجوب والحببات	1
Logenges – Troches- Pastills Molded Tablets	الأقراص السكرية والأقراص القالية	2
Granules	المثيرات	3
Capsules	الكبسولات	4
Compressed tablets 1	المضغوطات 1	5
Compressed tablets 2	المضغوطات 2	6
Compressed tablets Types 1	الأنواع المختلفة للمضغوطات 1	7
Compressed tablets Types 2	الأنواع المختلفة للمضغوطات 2	8
Compressed tablets Types 3	الأنواع المختلفة للمضغوطات 3	9
Manufacturing Defects of Tablets	مشاكل تصنيع المضغوطات	10
Sugar Coating	التلبيس السكري	11
Film Coating	التلبيس بالطبقة الرقيقة 1	12
Controlled released compressed tablets	المضغوطات ذات التحرر المعدل	13
Some Tablets Formulations	بعض الأمثلة لصياغة المضغوطات	14

### Ideal characters of coating material

1. Solubility in the coating solution
2. Solubility required for intended use- Free water solubility, Slow water solubility, pH- dependent solubility
3. Capacity to produce elegant looking product
4. Stability in presence of water, heat, moisture, air, and substrate being coated and no change in properties with aging.
5. Essentially no color, odor, or taste
6. Compatibility with common coating solution additives
7. Nontoxic and ease of application
8. Resistance to cracking and should act as barrier
9. Ease of printing procedure on high-speed equipment
10. Low cost & Ease of application without specialized equipment



## المضغوطات الملبيسة؟

### I. Therapy

- Avoid irritation of oesophagus and stomach
- Avoid bad taste
- Avoid inactivation of drug in the stomach
- Improve drug effectiveness
- Prolong dosing interval
- Improve dosing interval
- Improve patient compliance

5

تكنولوجيا صيدلانية 1

### II. Technology

- Reduce influence of moisture
- Avoid dust formation
- Reduce influence of atmosphere
- Improve drug stability
- Prolong shelf life

6

تكنولوجيا صيدلانية 1

### III. Marketing

- Avoid bad taste
- Improve product identity
- Improve appearance and acceptability

انواع التلبيس؟

- There are three main types of tablet coating:
  - Film coating
  - Sugar coating
  - Press coating



المبدأ العام للتلبيس: تطبيق مجموعة من المواد المُلِبِّسة  
 (السائلة) الساخنة على طبقة من النوى المتحركة بوجود  
 تيار من الهواء الساخن


## Film Coating

- This is the more modern of the two major coating processes.
- First introduced to the pharmaceutical industry in the 1950's

## التبسيس بالفلم

- العملية التي يتم خلالها إحاطة نواة صلبة بطبقة بوليمرية رقيقة (20-200 ميكرون).
- باستخدام أو وعية تبسيس تقليدية Conventional panning أو وعية تبسيس خاص Specialized equipment

## ■ Standard coating pan




تكنولوجيا صيدلانية ١

11

## Core

**Powders, granules, pellets, tablets,  
capsules**



تكنولوجيا صيدلانية ١

12

## Core

---

### Properties

#### *Hardness*

- Sufficient hardness ( $> 8 \text{ kg}$ ) and less friability ( $< 0.5 \%$ ) or ( $< 0.1 \%$ )
- **Less hardness** is required for sugar coating

## المواد المكونة لسائل التلبيس


**1- Polymer**


**2- Plasticizer**

**3- Colorants and Pigments**

**الماء أو محل عضوي مناسب:**  
 تكون مواد التلبيس من حلبة أو معلقة  
(**Solution or Suspension**)


## أنواع البوليمرات







# Block Copolymers

- 1- كتل بوليميرية ثنائية : Diblock copolymers
  - 2- كتل بوليميرية ثلاثة : Triblock copolymers
  - 3- كتل بوليميرية رباعية : Tetrablock copolymers







# تشكل الفلم Film Formation



**Fig. 5** Film formation from pseudolatex. (From Ref. 7)



## Film Coating

- **Polymeric films can be produced from:**
- A. Organic solutions of polymers**
- B. Aqueous pseudolatex Colloidal dispersions of polymer particles (10-500 nm).**

تكنولوجيا صيدلانية 1

23

## تصنيف أجهزة التلبيس

**Perforated pan**  
قدر تلبيس مثقب

Accela Cota✓  
Hi Cota✓

**Standard pan**  
قدر تلبيس تقليدي



Driam Coatig Pan✓  
Pellegrine Cota✓



Air Fluidize Coater Pan✓

التلبيس بالسرير الهوائي

تكنولوجيا صيدلانية 1

24





## تشكل الفلم Film Formation

طبيعة الفلم المتشكل تتفاوت بحسب البوليمر المستخدم  
وطبيعة السائل المرزوز وفق ما يلي:

✓ اختلاف في بنية الفلم ومظهره

✓ اختلاف في النفوذية

✓ الحاجة لعمليات معالجة حرارية

(Post coating thermal treatment)

✓ قدرة الفلم على تغيير آلية التحرر

## تشكل الفلم Film Formation

A. البوليمر المنحل بمحلات عضوية:

➢ ارزاز محلول التلبيس فوق النوى

➢ تبلل أسطح النوى

➢ توزع وتشابك والتصاق البوليمر بالأسطح

➢ تبخر محل التدريجي وتشكل الفلم

➢ ازدياد سماكة الفلم باستمرار ارزاز محلول التلبيس

## Film Formation تشكيل الفلم

B. البوليمرات المبعثرة بالماء: Pseudolatex system

- ▷ ارزاز محلول التلبيس المائي الغرويدي فوق النوى
- ▷ حجم حبيبات محلول ما بين 0.1-0.2 ميكرون
- ▷ تبلل أسطح النوى
- ▷ توزع وتشابك والتصاق البوليمر بالأسطح
- ▷ تبخر محل التدريجي يزيد التوتر السطحي بين البوليمر والماء ويدفع جزيئات البوليمر لترتخص وتشكل الفلم
- ▷ ازدياد سماكة الفلم باستمرار ارزاز محلول التلبيس

## Film Formation تشكيل الفلم

هناك نوعان من التلبيس بالفلم وفقاً للطبيعة البوليمر المستخدم:

**1- التلبيس اللاوظيفي Non-functional Coating**

**2- التلبيس الوظيفي Functional Coating**

## Film Formation

**أنواع البوليمرات المستخدمة في التلبيس اللاوظيفي:**

### 1- Cellulose derivatives:


- **Hydroxypropyl Methylcellulose HPMC,**
- **Hydroxypropylcellulose HPC,**
- **Hydroxyethylcellulose HEC,**
- **Methylcellulose MC,**
- **Ethylcellulose EC,**
- **Sodium carboxymethylcellulose NaCMC**

تكنولوجيا صيدلانية 1

33

*Polymers for conventional coating*

### - cellulose ethers



$R = H, CH_3, CH_3CH(OH)CH_2$

$R = H, [CH_3CH(OH)CH_2]_mH$

$R = CH_2CH_3$

$R = CH_2COONa$

HPMC

HPC

EC

NaCMC

تكنولوجيا صيدلانية 1

34

**Table 15** Commonly Used Polymers

Polymer	Comments
MC	Soluble in cold water, GI fluids, and a range of organic solvents.
EC	Soluble in organic solvents [insoluble in water and GI fluids. Used alone in modified-release formulations and in combination with water-soluble celluloses for immediate-release formulations.]
HEC	Soluble in water and GI fluids.
MHEC	Soluble in water and GI fluids. Has similar film-forming properties to HPMC, but is less soluble in organic solvents, which limited its popularity when solvent coating was the norm.
HPC	Soluble in cold water, GI fluids, and polar solvents [Becomes tacky when dried, so is unsuitable for use alone, often used in combination with other polymers to optimize adhesion of coat.]
HPMC	Soluble in cold water, GI fluids, alcohols, and halogenated hydrocarbons [Excellent film former] and the most widely used polymer [Can be used with lactose to improve adhesiveness.]
NaCMC	Soluble in water and polar solvents.

Abbreviations: MC, methylcellulose; EC, ethylcellulose; HEC, hydroxyethylcellulose; MHEC, methyl hydroxyethylcellulose; HPC, hydroxypropyl cellulose; HPMC, hydroxypropyl methylcellulose; NaCMC, sodium carboxymethylcellulose; GI, gastrointestinal.

تنخفض  
النفوذية

CMC.Na  
CMC-HEC  
HEC  
MC  
HEMC  
HPMC  
HPC  
MEC

تزداد الانحلالية  
والتشerd

## Film Formation تشكيل الفلم

- 2- **Vinyls (Polyvinyl pyrrolidone, PVP)**
- 3-**Glycols (Polyethylene glycols, PEG's 4000-20000)**
- 4-**Acrylic polymers Eudragit E pH<5**

معظم هذه البوليمرات منحلة في الماء عدا:  
 (EC and acrylate derivatives)  
 تعطي تلبيس لا وظيفي باستخدام طبقة تلبيس رقيقة أو  
 بمزجها مع مواد منحلة

## Film Formers

- التلبيس الوظيفي Functional Coating القادر على تغيير مكان التحرر (Modified release) والذي يصنف وفق الـ USP لنوعين هما:

- 1. Extended release:** One that permits at least a **twofold** reduction in the dosing frequency as compared to the situation in which the drug is presented as a conventional dosage form.
- 2. Delayed release:** One that releases the active ingredient at some time other than **promptly after administration** (enteric coated products for example).

## *Extended-release Oral Dosage Forms*

المواصفات المثالية للمادة الفعالة القابلة للتقديم كمضغوطة مطولة التأثير:

- They exhibit neither very slow nor **very fast rates of absorption and excretion**
- They are **uniformly absorbed** from the **G.I.T.**
- They are **administered in relatively small doses.**
- They possess a good **margin of safety** i.e. **Therapeutic Index (TI)**

تكنولوجيا صيدلانية 1

39

## Film Formers

الأنواع المختلفة من البوليميرات المستخدمة في التلبس الوظيفي المعوي تشمل:

- **Enteric polymers** المعوي التلبس
  1. **Natural polymers (Shellac)**
  2. **Cellulosic :**
    - **Cellulose Acetate Phthalate CAP**
    - **Cellulose Acetate Trimellitate CAT**
    - **Hydroxypropyl MethylCellulose Phthalate HPMCP,**
    - **Hydroxypropyl Methylcellulose Acetate Succinate HPMAS**
  3. **Acrylic (Poly (Methacrylate – Ethylacrylate) 1:1, Poly (Methacrylic acid – methyl methacrylate) 1:1)**

تكنولوجيا صيدلانية 1

40


**Table 17** Commonly Used Enteric-Coating Polymers

Polymer	Solubility profile	Comments
Shellac	Above pH 7	The original enteric-coating material, originally used in sugar-coated tablets. The high pH required for dissolution may delay drug release. Natural product that exhibits batch-to-batch variability.
CAP	Above pH 6	The high pH required for dissolution is a disadvantage. Forms brittle films, so must be combined with other polymers.
PVAP	Above pH 5	
HPMCP	Above pH 4.5	
Polymers of methacrylic acid and its esters	Various grades available with dissolution occurring above pH 6	Optimal dissolution profile for enteric coating. HP50 ← → HP55

*Abbreviations:* CAP, cellulose acetate phthalate; PVAP, polyvinylacetate phthalate; HPMCP, hydroxypropylmethylcellulose phthalate.

تکنولوجیا صیدلانیہ 1

41



$\mathbf{R}_1 = -\text{CH}_3$ ,  $\mathbf{R}_2 = -\text{CH}_3$  and  $\mathbf{R}_3 = -\text{COOH}$  (Eudragit® L and S)

$R_1 = -CH_3$ ,  $R_2 = -CH_2-CH_3$  and  $R_3 = -COOH$  (Eudragit® L100-55 and L30D-55)

$R_1 = -CH_3$ ,  $R_2 = -CH_3$  and  $R_3 = -COOCH_3$  (Eudragit® NE30D)

$R_1 = -CH_3$ ,  $R_2 = -CH_3$  and  $R_3 = -COOCH_2CH_2N^+(CH_3)_3Cl^-$  (Eudragit<sup>®</sup> RL and RS).

Figure 17: Structure chimique de l'Eudragit® (Vandamme *et al.*, 2002).

1 تكنولوجيا صيدلانية

42

**Table 1** Chemical Structure and Characteristics of Soluble Methacrylate Copolymers

Monomers	Methylmethacrylate (MMA)	Butylmethacrylate (BMA)	Dimethyaminoethyl methacrylate (DMAEMA)	Methacrylic acid (MAA)
Scientific name (IUPAC)	Structure	Solubility	Eudragit® types	Commercial forms
Poly(butyl methyl methacrylate-co-(2-dimethylaminoethyl)methacrylate-co-methyl methacrylate) 1:2:1, 150,000	MMA-BMA-DMAEMA = 25:25:50	Below pH 5.0	E 100 E PO E 12.5	Granules Powder Organic solution
Poly(methacrylic acid-co-ethyl acrylate) 1:1, 250,000	EA-MAA = 50:50	Above pH 5.5	L 30 D-55 L 100-55	Aqueous dispersion Powder
Poly(methacrylic acid-co-methyl methacrylate) 1:1, 135,000	MMA-MAA = 50:50	Above pH 6.0	L 100 L 12.5	Powder Organic solution
Poly(methacrylic acid-co-methyl methacrylate) 1:2, 135,000	MMA-MAA = 70:30	Above pH 7.0	S 100 S 12.5	Powder Organic solution
Poly(methylacrylate-co-methyl methacrylate-co-methacrylic acid)	MMA-MA-MAA = 25:65:10	Above pH 7.0	FS 30 D	Aqueous dispersion

تكنولوجيا صيدلانية ١



43

**Q38** Which of the following can be used as a binder in aqueous and non-aqueous systems?

- A  polymethacrylates
- B  acacia
- C  starch
- D  sucrose
- E  alginic acid

تكنولوجيا صيدلانية ١

44



## Film Formers

**الأنواع المختلفة من البوليميرات المستخدمة في التلبيس الوظيفي مطول التحرر تشمل:**

■ **Polymers used in extended release film coating include**

1. Natural polymers (Zein),
2. Cellulosic polymers (Ethylcellulose)
3. Silicone elastomers
4. Acrylic esters.

**TABLE 33.15 Examples of common materials used in extended-release coating formulations**


Coating material	Membrane characteristics
Fats and waxes (beeswax; carnauba wax; cetyl alcohol; cetostearyl alcohol)	<ul style="list-style-type: none"> <li>• Permeable and erodible</li> </ul>
Shellac	<ul style="list-style-type: none"> <li>• Permeable and soluble (at high pH)</li> </ul>
Zein	<ul style="list-style-type: none"> <li>• Permeable and soluble (at high pH)</li> </ul>
Ethylcellulose	<ul style="list-style-type: none"> <li>• Permeable and water-insoluble</li> </ul>
Cellulose esters (e.g., acetate)	<ul style="list-style-type: none"> <li>• Semi permeable and water insoluble</li> </ul>
Acrylic ester copolymers	<ul style="list-style-type: none"> <li>• Permeable and water insoluble</li> </ul>

**Table 2** Chemical Structure and Characteristics of Insoluble Methacrylate Copolymers

	H	CH <sub>3</sub>	CH <sub>3</sub>	
	C=CH <sub>2</sub>	C=CH <sub>2</sub>	C=CH <sub>2</sub>	
	C=O	C=O	C=O	
	O-C <sub>2</sub> H <sub>5</sub>	O-CH <sub>3</sub>	O-C <sub>2</sub> H <sub>5</sub> -N+(CH <sub>3</sub> ) <sub>3</sub> Cl	
Monomers	Ethyl acrylate (EA)	Methyl methacrylate (MMA)	Trimethylammonioethyl methacrylate clorid (TMAEMA)	
Scientific name	Structure	Permeability	Eudragit® types	Commercial forms
Poly(ethyl acrylate-co-methyl methacrylate) 2:1, 800,000	MMA-EA = 30:70	Medium	NE 30 D NE 40 D NM 30 D	Aqueous dispersion Aqueous dispersion Aqueous dispersion
Poly(ethyl acrylate-co-methyl methacrylate) 2:1, 600,000	MMA-EA = 30:70	Medium		
Poly(ethyl acrylate-co-methyl methacrylate-co-trimethylammonioethyl methacrylate chloride) 1:2:0.2, 150,000	MMA-EA-TMAEMA = 60:30:10	High	RL 100 RL PO RL 30 D RL 12.5	Granules Powder Aqueous dispersion Organic solution
Poly(ethyl acrylate-co-methyl methacrylate-co-trimethylammonioethyl methacrylate chloride) 1:2:0.1, 150,000	MMA-EA-TMAEMA = 65:30:5	Low	RS 100 RS PO RS 30 D RS 12.5	Granules Powder Aqueous dispersion Organic solution


تكنولوجيَا صيدلانية ١

49

**Figure 2** Water vapor permeability of pharmaceutical coating materials, measured according to DIN 53122 with isolated films of 25 µm thickness. Abbreviation: HPMC, hydroxypropyl methylcellulose.

تكنولوجيَا صيدلانية ١

50



51

Polymer	Threshold pH
Eudragit® L100	6.0
Eudragit® S100	7.0
Eudragit® L-30D	5.6
Eudragit® FS 30D	6.8
Eudragit® L100-55	5.5
Poly vinyl acetate phthalate	5.0
Hydroxypropyl methyl cellulose phthalate	4.5-4.8
Hydroxypropyl methyl cellulose phthalate 50	5.2
Hydroxypropyl methyl cellulose phthalate 55	5.4
Cellulose acetate trimellitate	4.8
Cellulose acetate phthalate	5.0

تكنولوجيابيسيلاستيكية 1

52

### الطرق المختلفة لتحضير أشكال فموية صلبة موجهة للقولون

العيوب	مثال	النظام
*تشابههـ الـ pH عند نهاية الأمعاء الدقيقة وببداية القولون. **الاختلافات الفيزيولوجية لـ pH.	Eudragit® L (pH= 6) Eudragit® S (pH= 7) Eudragit® FS (pH= 7) HPMCP (pH= 5)	بوليمر تحل اعتماداً علىـ الـ pH pH –dependent
*فترـة العبور والوصول للقولون غير ثابتـة **فترـة العبور ضمن القولون أكثر سرعة عند المرضى.	Eudragit® RL Eudragit® NE Eudragit® RS	بوليمر لا تعتمد علىـ الـ pH pH – independent
*الصيام والمرض يؤثر على النشاط البكتيري. **تأثير البكتيريا على استقلالية بعض المواد الفعالة.	Amylose Chitosan Dextran Pectine	بوليمر تحل بواسطة بكتيريا القولون

تكنولوجيا صيدلانية 1

53


## Formulation Components

In addition to the film – forming polymers, other **components may be included** in the coating formulation for different purposes.

- **Some of these components may be added to improve the film quality in terms of coalescence and/or facilitate large-scale production (e.g. plasticizers, surfactants and Antiadherents agents).**
- **Others are added to modify the film permeability properties to achieve a target release profile from the dosage form (e.g. pore formers or channeling agents).**

تكنولوجيا صيدلانية 1

54



### 3- Plasticizers

- Plasticizers are usually high – boiling point organic solvents that are used to impart flexibility to the otherwise hard or brittle polymeric materials.
- Plasticizers generally **cause a reduction in the cohesive intermolecular forces** along the polymer chains resulting in various changes in polymer properties, such as reduction in **tensile strength**, **increase in flexibility and reduction of polymer Tg** therefore enhancing the coalescence process and improving the integrity of the coat.

(Tg) درجة حرارة التحول الزجاجي للمواد: البوليمرات تكون صلبة وهشة تحت درجة حرارة الانتقال الزجاجية، ويمكن أن يحدث لها تشوه لدن (plastic deformation) عندما تكون درجة الحرارة أعلى منها. Tg غالباً ما تطبق على الحالة غير المتباعدة

١- تكنولوجيا صيدلانية

56

## Film Formation تشكيل الفلم

### 3-Plasticizer: الملدّنات:

- ✓ Swells and softens the polymer spheres,
- ✓ Facilitating coalescence
- ✓ Reducing minimum film formation temperature (MFT).
- ✓ The plasticizer reduces the glass transition temperature ( $T_g$ ) of the polymer.

( $T_g$ ) درجة حرارة التحول الزجاجي للمواد: البوليمرات تكون صلبة وشهة تحت درجة حرارة الانتقال الزجاجية، ويمكن أن يحدث لها تشوه لدن (plastic deformation) عندما تكون درجة الحرارة أعلى منها.  $T_g$  غالباً ما تطبق على الحالة غير المتبولة

تكنولوجيابا صيدلانية 1

57

## Film Formation تشكيل الفلم

- Glass transition temperature ( $T_g$ ) maybe defined as the temperature at which a polymer undergoes a marked change in material properties.
- Below  $T_g$ , the polymer is said to exist in the glassy state and is usually characterized by a somewhat ordered structure in which there is minimal polymer chain movement.
- Above  $T_g$ , the polymer is in a rubbery state, which is characterized by amorphous portions or regions with increased polymer chain movement and polymer elasticity.

تكنولوجيابا صيدلانية 1


58

## Plasticizers

- **منحلة في الماء Water soluble:** Glycerin, propylene glycol, low molecular weight polyethylene glycols (PEG 200 and 400). Triethyl citrate (TEC) (Citroflex®) and surfactants such as Tweens.
- **غير منحلة في الماء Water insoluble:** Acetyl triethyl citrate (ATEC), Acetyl tributyl citrate (ATBC), Dibutyl phthalate (DBP), Diethyl phthalate (DEP), Tributyl citrate (TBC).

تكنولوجيا صيدلانية 1

59



## 7 Applications in Pharmaceutical Formulation or Technology

Tributyl citrate is used to **plasticize** polymers in formulated pharmaceutical **coatings**. The coating applications include capsules, tablets, beads, and granules for taste masking, immediate release, sustained-release, and enteric formulations.<sup>(1-6)</sup>

## Plasticizers

- **Water insoluble:** Oils such as **oleic acid**, **caster oil** and **coconut oil**. **Surfactants** such as **Spans**.
- **With aqueous polymer** dispersions, water-soluble plasticizers dissolve whereas water-insoluble plasticizers have to be **emulsified in the aqueous phase of the dispersion.**

## Plasticizers

- **Surfactants** can be “**endogenous**” to the polymeric aqueous dispersion **since** they are used in the **synthesis** of some coating polymers (e.g. **Nonoxynol 100\*** in **Eudragit® NE 30D**) by emulsion polymerization.
- “**Exogenous**” surfactants may be added to the coating formulation to **facilitate the spreading** of the coating droplets on the surface of the substrate. They **lower interfacial tension** between organic polymer solution and the **aqueous phase during pseudolatex formation.**

\* series of polyoxyethylene ethers with lauryl side

## Pore Formers مشكل القنوات

- Film coats made of impermeable or semi-permeable polymers may be combined with **water-soluble pore formers such as micronized sucrose, sorbitol, lactose, NaCl and Calcium phosphate.**
- Upon contact with dissolution fluids, the pore former **leaches out rapidly** to form a multiporous rate-controlling membrane through which the drug diffuses **in a zero order fashion.**
- **pH dependent pore forming** agents are used in enteric coated substrates.

تكنولوجيا صيدلانية 1

63

## Filler الحشوة

عمل مساحيق التحميل

- خفض الانظام الذري للبلمر
- تباعد الذرات (كما الملدن)

➢ يزيد من كثافة الفلم و مقاومته الميكانيكية و خصائصه الفيزيوكيميائية

### 1- محبة للماء:

- ✓ أكسيد التيتان\*\*: خامل و غير سام نلاحظ عدم تجانس الطبقات الأولى من التلبيس يعطي تجانس لوني في النهاية، بنسبة مرتفعة ينتج تشقق والحل بإضافة الـ PEG (وزن مرتفع)
- ✓ الإيروزيل: غير سام و ناعم جداً غير منحل في الماء (تحل قلوية +)

✓ كربونات الكالسيوم: قليل الاستعمال و يمتص الماء أثناء الحفظ (تحل الحمضية)

تكنولوجيا صيدلانية 1 64

## الحشوة Filler

### 2-كارهة للماء:

- ✓ التالك: يعطي أفلاماً نصف شفافة و بالتالي تقل الحماية على النور وينقص من نفوذية بخار الماء و بذلك يزيد من حفظ الأدوية التي تتخرب بالرطوبة.
- ✓ شمعات المغنيزيوم: كاره للماء و تغطية كبيرة و أقل نفوذية لبخار الماء (أفضل من التالك) وبالتالي يبطئ من سرعة التحرر

## الملونات Colorants

### تصنيف الملونات حسب المنشأ

#### 1- الملونات الطبيعية :

- ذات المنشأ النباتي كاروتين (E160)
- الحيواني كوشينيل أو كارمين (E120)
- المنشأ المعدني (Pigment): أكسيد التينان (E171) ، أكسيد الحديد (E172)، كربونات الكالسيوم (E170)،  
(E173) Aluminum

#### 2- الملونات العضوية الصناعية (Dyes) :

amarant Tartrazine (E123) Amaranth (E102)

: ملون منحل بالماء محمل على مسحوق Pigment lake

## مراقبة التلبيس بالفلم

1- القساوة : ++

2- الهاشة: %0

3- شكل التلبيس: استمراره - انتظامه - تجانسه - لمعانه - نقاط التقشر - شكل السطح (مقبب)

4- مراقبة التلبيس:

1-4- استمرار التلبيس:

➢ طريقة الزئبق: تحت الضغط- 50 مضغوطة

➢ طريقة اليود: محلول اليود- 10 مضغوطة 3- 4 دقائق

### 2-4- تجسس التلبيس

3- سماكة الفلم: 50 مضغوطة - فرق السماكة قبل وبعد

4-4- مراقبة النفوذية:


➢ النفوذية على الهواء

➢ النفوذية على بخار الماء

5-4- ذوبان الفلم:

➢ تلبيس معدني

➢ تلبيس معوي



**Table 2.12: Disintegration time limits of different types of tablets and the disintegration medium.**

Type of tablets	Disintegration time	Disintegration medium	Temperature
Uncoated tablets	15 minutes	water, unless otherwise specified	$\pm 37^\circ\text{C}$
Dispersible/ soluble tablets	3 minutes	-do-	$25 \pm 1^\circ\text{C}$
Film coated tablets	30 minutes	-do-	$37 \pm 2^\circ\text{C}$
Other coated tablets	60 minutes*	-do-	-do-
Enteric coated tablets	60 minutes**	mixed phosphate buffer	-do-
Effervescent	5 minutes***	water	$25 \pm 5^\circ\text{C}$

\* For repeat test use 0.1 M Hydrochloric acid.

\*\* Prior to this test the tablets are subjected to disintegration test using 0.1 HCl and no tablet should disintegrate or even crack during 120 minutes.

\*\*\* Tablets should disintegrate without agitation.

**Table 2.18: Type of capsule, disintegration time limits, disintegration medium and temperatures**

Type of capsules	Time limit for disintegration	Disintegration medium	Temperature ( $^\circ\text{C}$ )
Hard gelatin capsules	30 minutes	Water (unless otherwise mentioned)	$37 \pm 2$
Soft gelatin capsules	60 minutes	-do-	-do-
Enteric capsules	60 minutes*	Mixed phosphate Buffer pH 6.8	-do-
Enteric capsules	60 minutes	Mixed phosphate Buffer pH 6.8	-do-

\* Prior to phosphate buffer the capsules are subjected to the test for two hours using 0.1 M Hydrochloric acid as the medium and no capsule show any sign for disintegration or rupture allowing the contents to escape.

**Table 4.5 Components of Nonaqueous Film-Coating Solutions**

Component	Example
Film former	Cellulose acetate phthalate
Alloying substance	Polyethylene glycol (less valuable material)
Plasticizer	Caster oil
Surfactant	Polyoxyethylene sorbitan derivatives
Opaquants	Titanium dioxide
Colorants	Dyes
Sweeteners	Saccharin
Flavors	Vanillin
Aromas	Vanillin
Glossants	Beeswax
Volatile solvent	Alcohol-acetone mixture

تكنولوجيا صيدلانية 1

71

**Table 4.6 Components of Aqueous Film-Coating Solutions**

Component	Example
Film forming polymer	Cellulose ether polymers (methylcellulose, hydroxypropylcellulose, hydroxypropylmethylcellulose)
Plasticizer	Glycerin, glycetyl triacetate (triacetin), dimethyl (or ethyl or butyl) phthalate, di-(2-ethylhexyl) (or butyl) adipate, dibutyl cebacate, dibutyl subacetate, propylene glycol, polyethylene glycol, oleic acid
Opacifier	Iron oxide pigments
Colorant	Dyes
Vehicle	Water

تكنولوجيا صيدلانية 1

72